

TRANSMITTAL LETTER TO THE UNITED STATES
 DESIGNATED/ELECTED OFFICE (DO/EO/US)
 CONCERNING A FILING UNDER 35 U.S.C. 371

Attorney's Docket Number
 08130.0058

U.S. Application No.
097719303

International Application. No.
 PCT/IB99/01001

International Filing Date
 June 3, 1999

Priority Date Claimed
 June 11, 1998

Title of Invention: OPTICAL COMPONENT, ORIENTATION LAYER, AND LAYERABLE POLYMERISABLE MIXTURE

Applicants For DO/EO/US: MARTIN SCHADT and Hubert SEIBERLE

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. [X] This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.
2. [] This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.
3. [] This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. [X] A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. [X] A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. [X] is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. [X] has been transmitted by the International Bureau.
 - c. [] is not required, as the application was filed in the United States Receiving Office (RO/US).
6. [] A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. [X] Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)).
 - a. [] are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. [] have been transmitted by the International Bureau.
 - c. [] have not been made; however, the time limit for making such amendments has NOT expired.
 - d. [X] have not been made and will not be made.
8. [] A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. [X] An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. [] A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11. to 16. below concern other document(s) or information included:

11. [X] An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. [X] An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. [X] A FIRST preliminary amendment.
- [] A SECOND or SUBSEQUENT preliminary amendment.
14. [] A substitute specification.
15. [] A change of power of attorney and/or address letter.
16. [X] Other items or information:
 - a. [] Verified Small Entity Statement.
 - b. [] Copy of Notification of Missing Requirements.
 - c. [X] Cover sheet of WIPO publication (W0 99/64924)(1-sheet).

U.S. APPLICATION NO.

09/719303

INTERNATIONAL APPLICATION NO.

PCT/IB99/01001

ATTORNEY DOCKET NUMBER

08130.0058

17. [X] The following fees are submitted:

Basic National Fee (37 CFR 1.492(a)(1)-(5)):

Search Report has been prepared by the EPO or JPO.....\$860.00
 International preliminary examination fee paid to
 USPTO (37 CFR 1.482).....\$690.00
 No international preliminary examination fee paid to
 USPTO (37 CFR 1.482) but international search fee
 paid to USPTO (37 CFR 1.445(a)(2)).....\$760.00
 Neither international preliminary examination fee
 (37 CFR 1.482) nor international search fee
 (37 CFR 1.445(a)(2)) paid to USPTO.....\$1,000.00
 International preliminary examination fee paid to USPTO
 (37 CFR 1.482) and all claims satisfied provisions
 of PCT Article 33(1)-(4).....\$ 100.00

CALCULATIONS

ENTER APPROPRIATE BASIC FEE AMOUNT**= \$ 860.00**

Surcharge of \$130.00 for furnishing the oath or declaration later than
 [] 20 [] 30 months from the earliest claimed priority date
 (37 CFR 1.492(e)).

\$

Claims	Number Filed	Number Extra	Rate	
Total Claims	29 - 20 =	9	X \$18.00	\$ 162.00
Independent Claims	1 - 3 =		X \$80.00	\$
Multiple dependent claim(s) (if applicable)			+\$270.00	\$

TOTAL OF ABOVE CALCULATIONS**= \$ 1022.00**

Reduction by 1/2 for filing by small entity, if applicable.

\$

SUBTOTAL**= \$ 1022.00**

Processing fee of \$130.00 for furnishing the English translation later
 than [] 20 [] 30 months from the earliest claimed priority date
 (37 CFR 1.492(f)).

\$

TOTAL NATIONAL FEE**= \$ 1022.00**

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The
 assignment must be accompanied by an appropriate cover sheet
 (37 CFR 3.28, 3.31).

\$40.00 per property

+

\$ 40.00

TOTAL FEES ENCLOSED**=****\$ 1062.00**

Amount to be

refunded


\$

charged

\$

- a. [X] A check in the amount of \$ 1062.00 to cover the above fees is enclosed.
 b. [] Please charge my Deposit Account No. _____ in the amount of
 \$ _____
 to cover the above fees. A duplicate copy of this sheet is enclosed.
 c. [X] The Commissioner is hereby authorized to charge any additional fees
 which may be required, or credit any overpayment to Deposit Account
 No. 06-0916. A duplicate copy of this sheet is enclosed.

The Commissioner is hereby authorized to charge any other fees due under 37 C.F.R. §1.16
 or §1.17 during the pendency of this application to our Deposit Account No. 06-0916.

SEND ALL CORRESPONDENCE TO:**Finnegan, Henderson, Farabow****Garrett & Dunner, L.L.P.****1300 I Street, N.W.****Washington, D.C. 20005-3315****EFC/FPD/mld**
Ernest F. Chapman

Reg. No. 25,691

Submitted: December 11, 2000

PATENT
Attorney Docket No. 08130.0058

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:)
)
Martin SCHADT et al.) Group Art Unit: Unassigned
)
Serial No.: Unassigned) Examiner: Unassigned
)
Filed: Filed Herewith)
)
For: OPTICAL COMPONENT, ORIENTATION LAYER, AND LAYERABLE
POLYMERISABLE MIXTURE, being a National Stage filing of PCT
International Application No. PCT/IB99/01001, filed on June 3, 1999

Assistant Commissioner for Patents
Washington, DC 20231

Sir:

Preliminary Amendment

Before examining this application, please amend the application as follows:

In the Specification:

Page 1, after the title, insert -- This application is a national stage filing under 35 U.S.C. § 371 of international application no. PCT/IB99/01001, filed on June 3, 1999, which published in the English language. --

In the Claims:

Please amend claims 1, 3-5, 7-19, 21, 23-26, and 28-29 as follows:

Claim 1, line 1, delete "An" and insert in its place -- A --.

Claim 3, line 2, delete "parts" and insert in its place -- part --.

Claim 4, line 2, delete "part" and insert in its place -- parts --.

Claim 5, line 1, delete "any of Claims 1 to 4" and insert in its place
-- Claim 1 --.

Claim 7, line 1, delete "any of Claims 1 to 4" and insert in its place
-- Claim 1 --.

- Claim 8, line 1, delete "any one of Claims 1 to 7" and insert in its place
-- Claim 1 --;
- line 2, delete "(I)" and insert in its place -- (i) --.
- Claim 9, line 1, delete "any of Claims 1 to 7" and insert in its place
-- Claim 1 --.
- Claim 10, line 1, delete "any of Claims 1 to 7" and insert in its place
-- Claim 1 --.
- Claim 11, line 1, delete "any preceding claim" and insert in its place
-- Claim 1 --;
- line 2, delete "Is/comprises" and insert in its place
-- is or comprises --.
- Claim 12, line 1, delete "any preceding claim" and insert in its place
-- Claim 1 --.
- Claim 13, delete "any preceding claim" and insert in its place -- Claim 1 --.
- Claim 14, delete "any preceding claim" and insert in its place -- Claim 1 --.
- Claim 15, delete "any preceding claim" and insert in its place -- Claim 1 --.
- Claim 16, delete "any preceding claim," and insert in its place -- Claim 1,
which is --.
- Claim 17, line 2, delete "any of Claims 1 to 16" and insert in its place
-- Claim 1 --.
- Claim 18, line 2, delete "any of Claims 1 to 16" and insert in its place
-- Claim 1 --.
- Claim 19, line 2, delete "any of Claims 1 to 16" and insert in its place
-- Claim 1 --.
- Claim 21, line 1, delete "or 20".
- Claim 23, line 1, delete "any of Claims 19 to 22" and insert in its place
-- Claim 19 --.
- Claim 24, line 1, delete "any of Claims 19 to 22" and insert in its place
-- Claim 19 --.
- Claim 25, line 1, delete "any of Claims 19 to 22" and insert in its place
-- Claim 19 --.
- Claim 26, line 2, delete "any of Claims 1 to 16" and insert in its place
-- Claim 1 --.

08130.0058

LAW OFFICES

FINNEGAN, HENDERSON,
FARABOW, GARRETT,
& DUNNER, L.L.P.
1300 I STREET, N. W.
WASHINGTON, DC 20005
202-406-4000

Claim 28, line 1, delete "or 27".

Claim 29, delete "any of Claims 26 to 28" and insert in its place -- Claim 26 --.

Remarks

Claims 1-29 are pending in this application. If there is any fee due in connection with the filing of this Preliminary Amendment, please charge the fee to our Deposit Account No. 06-0916.

Respectfully submitted,

FINNEGAN, HENDERSON, FARABOW,
GARRETT & DUNNER, L.L.P.

By: 

Steven J. Scott

Reg. No. 43,911

Date: December 11, 2000

0077606760

OPTICAL COMPONENT, ORIENTATION LAYER, AND
LAYERABLE POLYMERISABLE MIXTURE

5 This invention relates to a polymerisable mixture which can be applied as a layer, to an orientation layer of the mixture, and to an optical component (such as a retarder or a liquid crystal display) having a layer of which the mixture is a precursor.

10 Anisotropic transparent or coloured cross-linked polymer layers with three-dimensional orientation of the optical axis, either uniform or preset at individual places, are of great interest in many sectors of display technology, integrated optics etc.

15 For some years, substances having this property in principle have become known, namely certain cross-linkable liquid crystalline diacrylates and diepoxides. Before cross-linking, these substances can be orientated in the liquid crystalline phase in sandwich cells consisting, for example, of glass plates having an interposed monomer layer with the aid of conventional orientating layers on the two glass plate surfaces or under the influence of external fields, e.g. strong magnetic or electric fields, and in a second phase can be photo-cross linked in the cells such that the wall forces acting on
20 the two sides of the monomer layer, or the applied fields, preserve the preset orientation during the cross-linking process.

25 Cross-linked liquid crystalline monomers or oligomers or polymers are also referred to as LCPs (liquid crystal polymers) in the following text.

There have also become known methods which permit the production of orientation layers with locally variable orientating properties.

CONFIRMATION COPY

U.S. Patent No. 4,974,941 (Gibbons *et al.*) describes a process wherein a preferred direction is induced in response to exposure with linearly polarised light of an appropriate wavelength by the cis-trans-isomerisation of dyes. Liquid crystals in contact with a surface thus exposed are oriented in accordance with this preferred direction. This orientation process is reversible – i.e., by further exposure of the layer to light of a second polarisation direction the orientation direction can be rotated again.

In the case of the photostructurable orientation layers described in U.S. Patent No. 5,389,689 (Chigrinov *et al.*), an irreversible anisotropic polymer network is used. During the exposure to linearly polarised light, anisotropic orienting properties are induced in a photo-polymerisable layer and at the same time a polymer network is built up. Such linear photo-polymerised polymer networks (LPP), also known as photo-oriented polymer networks (PPN), are of use wherever stable, structured or unstructured liquid crystal orientation layers are required.

Layer structures comprising an anisotropic film of LCPs in contact with an orientating layer of a linear photo-polymerised polymer network (LPP) are described in U.S. Patent No. 5,602,661 (Schadt *et al.*). The manufacture of these layer structures is effected by orientation of the liquid crystal by interaction with the LPP layer and fixing the orientation in a subsequent cross-linking step. With this technique, it is even possible to manufacture multi-layer structures consisting of several oriented liquid crystal polymer layers, as is shown e.g. in European Application No. 0 689 084 (Schadt *et al.*).

As is well known, in addition to an azimuthal alignment, a tilt angle, i.e. an inclination of the optical axis of the liquid crystal layer relative to the plane of the layer, is often necessary. This can be achieved by an LPP orientation layer having a tilt angle on the surface, disclosed e.g. in European Application No. 0 756 193 (Schadt *et al.*).

To sum up, it can be said that LCP layers, usually in combination with orientation layers, are the basis of a large number of optical components like retarders, optical filters, polarizer etc. Layer structures of the type mentioned above with locally varying optical axes can also be used as a safeguard against counterfeiting and copying, as disclosed for example by European Application No. 0 689 065 (Schadt *et al.*).

Furthermore, it is well known to the artisan and understood in the present context that orientation layers are not only used for producing LCP components but also for aligning liquid crystals in liquid crystal displays, light valves etc.

The present invention provides and opens up new possibilities both for optical components, particularly of the aforementioned kind, and for liquid crystal orientation layers.

According to the invention, a polymerisable mixture comprises

- (i) a liquid crystal monomer or pre-polymer having cross-linkable groups;
and
- (ii) a photo-orientable monomer or oligomer or polymer.

Despite the distinct functions of the participating molecules, it has been surprisingly discovered that these mixtures are capable of being both oriented and cross-linked into a liquid crystal polymer. These mixtures are hence usable on the one hand as anisotropic layers in optical components or on the other hand, normally applied more thinly, as orientation layers.

This leads to various advantages hitherto unavailable.

In the case of an anisotropic layer for an optical component, only one layer need be applied instead of the hitherto necessary two, thus reducing the number of processing steps.

- 5 In the case of an orientation layer, the orientation proceeds not only at the surface of the layer but can proceed throughout its depth.

It is no longer necessary to apply and appropriately (e.g. imagewise) expose or irradiate an e.g. patterned orientation layer before the LCP layer is applied, in other words the entire layer-applying stage can be completed before the exposure/irradiation stage. These stages can be performed quite independently and even at separate locations. This is an important benefit for security purposes, where a secret alignment pattern is to be imposed on an LPP layer; the manufacturer who applies the LCP layer does not (as hitherto) need to be given the secret pattern, which improves the safeguards against counterfeiting.

Varying the types and proportions of the various chemical components of the mixtures according to the invention is a useful tool for influencing properties such as viscosity and coatability of the mixtures; for example, an unacceptable coalescence into globules of an applied layer of such a mixture can be inhibited by increasing its viscosity.

By "photo-orientable" is meant that the substance (ii) is capable of developing a preferred direction when irradiated with linearly polarised light and thus inducing an alignment of liquid crystals.

It is understood that substance (i) may also be an LCP mixture, i.e. may contain two or more different liquid crystal molecule types. Equally, substance (ii) may be a mixture of photo-orientable molecules.

Assuming that the cross-linkable liquid crystal substance (i) is present in an amount of 100 parts, the photo-orientable substance (ii) preferably is present in an amount of at least 0.1 part, more preferably of at least 1 part, most preferably of at least 10 parts.

- 5 A preferred photo-orientable substance (ii) comprises molecules showing a cis-trans-isomerism, particularly azo dyes.

Another preferred photo-orientable substance (ii) comprises a linearly photo-polymerisable monomer or oligomer or polymer.

10

Depending on the intended application, the cross-linkable liquid crystal substance (i) may have a nematic phase or cholesteric phase or a ferroelectric phase respectively.

The substance(s) (i) is/are preferably acrylate or diacrylate.

15

In a preferred embodiment of the invention, the mixture further comprises chiral molecules.

In another preferred embodiment, the mixture further comprises dye molecules.

20

In another preferred embodiment, the mixture further comprises dichroic molecules.

In another preferred embodiment, the mixture further comprises fluorescent molecules.

- 25 A presensitised film precursor according to the invention comprises a substrate (such as a plastic film) carrying a layer (e.g. 0.1 to 5 microns thick) of a mixture as set forth above.

Such a precursor can be manufactured in industrial-sized rolls and transported to the end user (in the dark). The applied layer should be able to withstand the rigours of transport, especially if protected by a peel-off layer.

- 5 A substrate carrying a layer of a mixture according to the invention, for many applications, should be conductive under the layer.

10 An optical component according the invention comprises a layer of a mixture as set forth above, in which the liquid crystal monomer or pre-polymer is at least partly polymerised. Such a layer usually will be optically anisotropic.

Preferably, the layer has a preferred orientation direction or locally varying preferred orientation directions, which may be at an angle to the plane of the substrate, in other words with a tilt angle.

15 The thickness of the layer will depend on the use. Thus, for an optical component intended to be used in its own right, such as for instance a retarder, an optical filter, a polarizer or a polarised light emitter, a relatively thick layer, e.g. 0.3 to 5 μm , is preferred. For a layer which is intended to act as an orientation layer without
20 significant inherent optical properties, a thinner coating such as 0.01 to 1 μm is preferred. Although photo-orientable compounds, particularly LPP compounds, can be used by themselves as orientation layers, the LCP compounds may advantageously confer networking forces retaining the preferred direction in the photo-orientable compounds.

25 A method according to the invention of making an at least partly polymerised, optically anisotropic layer of a mixture as set forth above comprises exposing the mixture (preferably in its isotropic phase, e.g. by warming it) to linearly polarised light (optionally in different orientations in different parts of the layer, for example in

imagewise, patternwise and pixellated arrangement) while maintaining such conditions that the polymerisation or cross-linking of substance (i) is essentially inhibited, whereby at least some of the molecules of the substance (ii) are photo-oriented. Initially, the molecules of substance (i), i.e. the liquid crystal prepolymers, must not cross-link.

5 However, once they have adopted the preferred orientation, and there is an adequate proportion of substance (ii) photo-oriented for this eventually to occur spontaneously, the molecules of substance (i) may be polymerised or cross-linked with (polarised or non-polarised) light in the anaerobic conditions (e.g. by purging oxygen with a flow of nitrogen or by vacuum). The differential polymerisation of (ii) then (i) may

10 alternatively be achieved by different wavelengths of exciting radiation, though the preferred method remains adjustment of the oxygen partial pressure.

According to the incident angle of the polarised light, a tilt angle can be built in which the liquid crystal molecules will adopt.

15 Under special conditions, the method may be modified in that the light used for the photo-alignment need not be polarised. If for example the layer is in a cholesteric phase, where the liquid crystal molecules organise themselves in a helical conformation, an alignment of the axes of the helices may be induced by the direction


20 of the incident light.

The invention will now be described by way of example.




Example 1

25 Making a solution of an LPP (linear photopolymerisable polymer)/LCP (liquid crystal polymer) mixture

—



5



10

Then an LPP/LCP mixture M1 was made from:

54.4 wt% = 224.0mg of Monomer 1

10.2% = 42.2mg of Monomer 2

15

29.2% = 120.2mg of LPP A

1.4% = 5.6mg of a photoinitiator (Irgacure (trade mark) 369 by CIBA), and
1.4% = 5.6mg of BHT (butyl hydroxy toluene) as an inhibitor.

A 5wt% solution of the mixture M1 was made in N-methyl-pyrrolidone (NMP), then
stirred for 30 minutes at 50C, and filtered through a 0.2µm filter.

Example 2

Making an Orientation Layer

The solution from Example 1 was thinly spin-coated at 2000 rpm onto two ITO
(indium-tin-oxide) coated glass plates, which were then dried for 30 minutes at 130C on
a hotplate.

The dried plates were warmed to 75C and irradiated for 6 minutes under ultraviolet
polarised light from a 200W mercury high pressure lamp and having an incident angle
of 70°. In this procedure, the direction of polarisation of the light lay in the plane
perpendicular to the plate and including the incident light direction. The polariser was a
film polariser HNP'B by Polaroid. The wavelength of the light was further limited by a
uv filter WG295 (Schott) and a bandpass filter UG11 (Schott). The intensity of the uv
light at the plate was determined as 2mW/cm².

After this irradiation, the layers were cooled at 1C/min to 65C, then at 5C/min to 50C.
The layers were still liquid.

The layers were then irradiated for ten minutes under nitrogen at room temperature by
isotropic (not-polarised) light from a mercury lamp at an intensity in the ultraviolet of
4.1mW/cm². Because of the presence of intervening glass (containing the nitrogen), the

incident light no longer included wavelengths below 350nm, which the glass had absorbed.

After this irradiation, the layers were no longer liquid but had become cross-linked.

5

Example 3

Making a parallel-sided cell

10 With the coated sides facing inwards, the two plates from Example 2 were assembled into a parallel-sided cell, using a glass fibre of 20µm thickness as a spacer. The cell was immediately filled with a nematic liquid crystal mixture MLC 12000-000 (Merck) at a temperature only just above the liquid crystal-isotropic transition temperature (considered to be 89C in this case), and slowly cooled.

15

Holding the filled cell between crossed polarisers showed that the liquid crystal mixture was uniformly oriented. Using a tilt compensator and a polarisation microscope, the orientation direction which the coated plates had imposed on the nematic liquid crystal mixture was established to be parallel to the direction of polarisation of the uv light
20 which had irradiated the plates.

The rotating crystal technique showed that the tilt angle adopted by the liquid crystal was a hefty 25°.

25

Example 4

Making a solution of an LPP (linear photopolymerisable polymer)/LCP (liquid crystal polymer) mixture

Example 1 was repeated, except that a 25wt.% solution of mixture M1 in NMP was used.

Example 5

5

Coating a Glass Plate

The solution from Example 4 was spin-coated at 1500 rpm onto a glass plate, which was then dried for 10 minutes at 130C on a hotplate. Observation through a polarisation microscope showed that the resulting layer was liquid crystalline but had no preferred orientation. Using a polarising microscope with a hotplate (Mettler FP5) the liquid crystal-isotropic transition temperature was measured as $T_c = 69C$.

Example 6

15

Making an optical retarder layer

The layer from Example 5 was warmed to 75C and irradiated for 3 minutes under ultraviolet polarised light from a 200W mercury high pressure lamp. The polariser was a film polariser HNP'B by Polaroid. The wavelength of the light was further limited by a uv filter WG295 (Schott) and a bandpass filter UG11 (Schott). The intensity of the uv light at the plate was determined as $2mW/cm^2$.

After this irradiation, the layer was cooled at 1C/min to 65C, then at 5C/min to 50C.

The layer was then removed from the hotplate and placed between crossed polarisers. The layer was now uniformly oriented. On rotating the substrate, it appeared, alternately, wholly dark or wholly light. Touching it established that the layer was still liquid.

09719303-12100
001121-160

The layer was then irradiated for ten minutes under nitrogen at room temperature by isotropic (not-polarised) light from a mercury lamp at an intensity in the ultraviolet of 4.1mW/cm^2 . Because of the presence of intervening glass (containing the nitrogen), the incident light no longer included wavelengths below 350nm, which the glass had absorbed.

After this irradiation, the layer was no longer liquid but had become firm and cross-linked. Its thickness was 670nm.

Using a tilt compensator and a polarisation microscope, the layer was found to have an optical retardation of 52.5nm. It was also established that the orientation of the optical axis all over the layer was parallel to the polarisation direction chosen in the first ultraviolet irradiation.

Example 7

Optical retarder layer with tilted optical axis

Example 5 was repeated. Before irradiation, the lower half of the glass plate was covered and the plate rotated 70° about an axis perpendicular to the plane containing the direction of incident light and its direction of polarisation. During irradiation with linearly polarised light, the temperature of the glass plate was held constant at 75°C , just as in Example 6. The duration of irradiation was selected to be six minutes, as the effective intensity of the light on the layer was reduced by the rotation of the glass plate.

After this first irradiation, the glass plate was rotated in the opposite direction so that the normal to the substrate surface now made an angle of -70° with the incident direction of the light. Also, now only the upper half of the plate was covered (so that

each half of the plate had only one irradiation). There now followed a second six-minute irradiation, of only the exposed lower half of the plate.

Thereafter, as in Example 6, the coating was slowly cooled and, again as in Example 6,
5 was crosslinked under nitrogen with isotropic ultraviolet light.

On observing the layer through crossed polarisers, a uniform orientation was apparent, leading to alternate lightening and darkening as the layer was rotated. Using a tilt compensator it was established, as in Example 6, that the optical axis was parallel to the
10 plane of polarisation of the linearly polarised ultraviolet light.

The substrate was then so disposed between crossed polarisers that the optical axis made an angle of 45° with the directions of polarisation. On tilting the substrate about an axis which was in the plane of the layer but perpendicular to the optical axis, it could
15 be seen that one half of the layer became darker and the other lighter. Reversing the tilt reversed and inverted the effect.

By obliquely illuminating with linearly polarised light, the molecules of the layer were preferentially orientated at an angle to the substrate surface, whereby the optical axis
20 was established with a tilt with respect to the surface.

CLAIMS:

1. An polymerisable mixture comprising
- 5 (i) a liquid crystal monomer or pre-polymer having cross-linkable groups;
and
(ii) a photo-orientable monomer or oligomer or polymer.
2. A mixture according to Claim 1, wherein the cross-linkable liquid crystal
10 substance (i) is present in an amount of 100 parts, and the photo-orientable
substance (ii) is present in an amount of at least 0.1 part.
3. A mixture according to Claim 2, wherein the photo-orientable substance (ii) is
present in an amount of at least 1 parts.
- 15 4. A mixture according to Claim 2, wherein the photo-orientable substance (ii) is
present in an amount of at least 10 part.
5. A mixture according to any of Claims 1 to 4, wherein the photo-orientable
substance (ii) comprises molecules showing a cis-trans-isomerism.
- 20 6. A mixture according to Claim 5, wherein the photo-orientable substance (ii)
comprises azo dyes.
7. A mixture according to any of Claims 1 to 4, wherein the photo-orientable
25 substance (ii) comprises a linearly photo-polymerisable monomer or oligomer or
polymer.
8. A mixture according to any one of Claims 1 to 7, wherein the cross-linkable
liquid crystal substance (I) has a nematic phase.

9. A mixture according to any of Claims 1 to 7, wherein the cross-linkable liquid crystal substance (i) has a cholesteric phase.
- 5 10. A mixture according to any of Claims 1 to 7, wherein the cross-linkable liquid crystal substance (i) has a ferroelectric phase.
11. A mixture according to any preceding claim, wherein the cross-linkable liquid crystal substance (i) is/comprises acrylate or diacrylate.
- 10 12. A mixture according to any preceding claim, further comprising chiral molecules.
13. A mixture according to any preceding claim, further comprising dye molecules.
- 15 14. A mixture according to any preceding claim, further comprising dichroic molecules.
15. A mixture according to any preceding claim, further comprising fluorescent molecules.
- 20 16. A mixture according to any preceding claim, dissolved in a solvent.
17. A presensitised film precursor, comprising a substrate carrying a layer of a mixture according to any of Claims 1 to 16.
- 25 18. A substrate having an electrically conductive surface which carries a layer of a mixture according to any of Claims 1 to 16.

19. An optical component comprising an at least partly polymerised layer of a mixture according to any of Claims 1 to 16.
20. An optical component according to Claim 19, wherein the layer is optically anisotropic.
21. An optical component according to Claim 19 or 20, wherein the layer is polymerised with a preferred orientation direction.
22. An optical component according to Claim 21, wherein the layer is polymerised with locally varying preferred orientation directions.
23. An optical component according to any of Claims 19 to 22, wherein the layer has the function of an orientation layer.
24. An optical component according to any of Claims 19 to 22, wherein the layer has the function of a retarder or an optical filter or a polarizer or a polarised light emitter.
25. An optical component according to any of Claims 19 to 22, wherein the layer has the function of an orientation layer as well as a retarder or an optical filter or a polarizer, or a polarised light emitter.
26. A method of making an at least partly polymerised, optically anisotropic layer of a mixture according to any of Claims 1 to 16, comprising
- (a) exposing the mixture to linearly polarised light while maintaining such conditions that the polymerisation or cross-linking of substance (i) is essentially inhibited, whereby at least some of the molecules of the substance (ii) are photo-oriented; and

- (b) allowing substance (i) to adopt the imposed orientation(s) and exposing the mixture to light, whereby at least some of the molecules of the substance (i) are polymerised or cross-linked.

- 5 27. A method according to Claim 26, wherein during step (a) the mixture is maintained in its isotropic phase.
28. A method according to Claim 26 or 27, wherein during step (a) the mixture is exposed to light of different directions of polarisation in different parts.
- 10 29. An optical component made by a method according to any of Claims 26 to 28.

1-00

Full Name of First Inventor	Inventor's Signature	Date
<u>Martin Schadt</u>	<i>Martin Schadt</i>	2. Nov 2000
Residence	Country of Citizenship	
<u>Seltisberg, Switzerland</u> CHX	Switzerland	
Post Office Address		
Liestalerstrasse 77, CH-4411 Seltisberg, Switzerland		

2-00

Full Name of Second Inventor	Inventor's Signature	Date
<u>Hubert Seiberle</u>	<i>Hubert Seiberle</i>	2. 11. 2000
Residence	Country of Citizenship	
<u>Weil am Rhein, Germany</u> DEX	Germany	
Post Office Address		
Bodenseestrasse 1, D-79576 Weil am Rhein, Germany		

007130.0058

DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that: My residence, post office address and citizenship are as stated below next to my name; I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

OPTICAL COMPONENT, ORIENTATION LAYER, AND LAYERABLE POLYMERISABLE MIXTURE

the specification of which:

is attached hereto; or

was filed as United States Application Serial No. **serial number**
on **filing date**, and was amended on _____
(if applicable); or

was filed as PCT International Application Number PCT/IB99/01001
on June 3, 1999 and was amended on _____
(if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above. I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56.

I hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate or § 365(a) of any PCT international application(s), designating at least one country other than the United States, listed below and have also identified below any foreign application(s) for patent or inventor's certificate, or any PCT international application(s) having a filing date before that of the application(s) of which priority is claimed:

Country	Application Number	Date of Filing	Priority Claimed Under 35 U.S.C. 119
Great Britain	9812636.0	June 11, 1998	<input checked="" type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO

I hereby claim the benefit under 35 U.S.C. § 119(e) of any United States provisional application(s) listed below:

Application Number	Date of Filing

I hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s) or § 365(c) of any PCT international application(s) designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT international application(s) in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application(s) and the national or PCT international filing date of this application:

Application Number	Date of Filing	Status (Patented, Pending, Abandoned)

I hereby appoint the following attorney and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. **FINNEGAN, HENDERSON, FARABOW, GARRETT & DUNNER, L.L.P.**, Reg. No. 22,540, Douglas B. Henderson, Reg. No. 20,291; Ford F. Farabow, Jr., Reg. No. 20,630; Arthur S. Garrett, Reg. No. 20,338; Donald R. Dunner, Reg. No. 19,073; Brian G. Brunsvold, Reg. No. 22,593; Tipton D. Jennings IV, Reg. No. 20,645; Jerry D. Voight, Reg. No. 23,020; Laurence R. Heffer, Reg. No. 20,827; Kenneth E. Payne, Reg. No. 23,098; Herbert H. Mintz, Reg. No. 26,691; C. Larry O'Rourke, Reg. No. 26,014; Albert J. Santorelli, Reg. No. 22,610; Michael C. Elmer, Reg. No. 25,857; Richard H. Smith, Reg. No. 20,609; Stephen L. Peterson, Reg. No. 26,325; John M. Romary, Reg. No. 26,331; Bruce C. Zotter, Reg. No. 27,680; Dennis P. O'Reilly, Reg. No. 27,932; Allen M. Sokal, Reg. No. 26,695; Robert D. Bajefsky, Reg. No. 25,387; Richard L. Stroup, Reg. No. 28,478; David W. Hill, Reg. No. 28,220; Thomas L. Irving, Reg. No. 28,619; Charles E. Lipsey, Reg. No. 28,165; Thomas W. Winland, Reg. No. 27,605; Basil J. Lewris, Reg. No. 28,818; Martin I. Fuchs, Reg. No. 28,508; E. Robert Yoches, Reg. No. 30,120; Barry W. Graham, Reg. No. 29,924; Susan Haberman Griffen, Reg. No. 30,907; Richard B. Racine, Reg. No. 30,415; Thomas H. Jenkins, Reg. No. 30,857; Robert E. Converse, Jr., Reg. No. 27,432; Clair X. Mullen, Jr., Reg. No. 20,348; Christopher P. Foley, Reg. No. 31,354; John C. Paul, Reg. No. 30,413; David M. Kelly, Reg. No. 30,953; Kenneth J. Meyers, Reg. No. 25,146; Carol P. Einaudi, Reg. No. 32,220; Walter Y. Boyd, Jr., Reg. No. 31,738; Steven M. Anzalone, Reg. No. 32,095; Jean B. Fordis, Reg. No. 32,984; Barbara C. McCurdy, Reg. No. 32,120; James K. Hammond, Reg. No. 31,964; Richard V. Burgujian, Reg. No. 31,744; J. Michael Jakes, Reg. No. 32,824; Dirk D. Thomas, Reg. No. 32,600; Thomas W. Banks, Reg. No. 32,719; Christopher P. Isaac, Reg. No. 32,646; Bryan C. Diner, Reg. No. 32,409; M. Paul Barker, Reg. No. 32,013; Andrew Chanho Sonu, Reg. No. 33,457; David S. Forman, Reg. No. 33,694; Vincent P. Kovalick, Reg. No. 32,867; James W. Edmondson, Reg. No. 33,871; Michael R. McGurk, Reg. No. 32,045; Joann M. Neth, Reg. No. 36,363; Gerson S. Panitch, Reg. No. 33,751; Cheri M. Taylor, Reg. No. 33,216; Charles E. Van Horn, Reg. No. 40,266; and Linda A. Wadler, Reg. No. 33,218; Jeffrey A. Berkowitz, Reg. No. 36,743; Michael R. Kelly, Reg. No. 33,921; James B. Monroe, Reg. No. 33,971; Doris Johnson Hines, Reg. No. 34,629; Allen R. Jensen, Reg. No. 28,224; Lori Ann Johnson, Reg. No. 34,498; and David A. Manspeizer, Reg. No. 37,540 and Steven J. Scott, Reg. No. 43,911. Please address all correspondence to **FINNEGAN, HENDERSON, FARABOW, GARRETT & DUNNER, L.L.P.**, 1300 I Street, N.W., Washington, D.C. 20005, Telephone No. (202) 408-4000.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.